

Sponsor: Jiri Kus NANOSPACE s.r.o. Rohova 98 Domazlice, 344 01 CZECH REPUBLIC

## Bacterial Filtration Efficiency (BFE) Final Report

Test Article: NANO BANDANA NECK GAITER NANOSPACE

Study Number: 1416615-S01 Study Received Date: 11 May 2021

Testing Facility: Nelson Laboratories, LLC 6280 S. Redwood Rd.

Salt Lake City, UT 84123 U.S.A.

Test Procedure(s): Standard Test Protocol (STP) Number: STP0004 Rev 18

Deviation(s): None

**Summary:** The BFE test is performed to determine the filtration efficiency of test articles by comparing the bacterial control counts upstream of the test article to the bacterial counts downstream. A suspension of *Staphylococcus aureus* was aerosolized using a nebulizer and delivered to the test article at a constant flow rate and fixed air pressure. The challenge delivery was maintained at  $1.7 - 3.0 \times 10^3$  colony forming units (CFU) with a mean particle size (MPS) of  $3.0 \pm 0.3 \, \mu m$ . The aerosols were drawn through a six-stage, viable particle, Andersen sampler for collection. This test method complies with ASTM F2101-19 and EN 14683:2019, Annex B.

All test method acceptance criteria were met. Testing was performed in compliance with US FDA good manufacturing practice (GMP) regulations 21 CFR Parts 210, 211 and 820.

Test Side: Inside BFE Test Area: ~7.8 cm<sup>2</sup>

BFE Flow Rate: 28.3 Liters per minute (L/min)

Conditioning Parameters:  $85 \pm 5\%$  relative humidity (RH) and  $21 \pm 5\%$  for a minimum of 4 hours

Test Article Dimensions: ~53 mm x ~32 mm

Positive Control Average: 2.5 x 10<sup>3</sup> CFU

Negative Monitor Count: <1 CFU

MPS: 2.8 µm





Mikell Goldsberry electronically approved

Mikell Goldsberry

08 Jun 2021 23:27 (+00:00)

Study Completion Date and Time

801-290-7500

Study Director

nelsonlabs.com

sales@nelsonlabs.com

FRT0004-0001 Rev 22 Page 1 of 2



## Results:

Test Article Number	Percent BFE (%)
1	98.5
2	98.4
3	98.8

The filtration efficiency percentages were calculated using the following equation:

$$\% BFE = \frac{C - T}{C} \times 100$$

C = Positive control average

T = Plate count total recovered downstream of the test article Note: The plate count total is available upon request

jhs