

Sponsor: Jiri Kus Nanospace s.r.o. Rohova 98 Domazlice, 344 01 CZECH REPUBLIC

## Viral Filtration Efficiency (VFE) Final Report

WASHABLE DESIGN NANO FACE MASK NANOSPACE Test Article:

Study Number: 1416611-S01 Study Received Date: 11 May 2021

Testing Facility: Nelson Laboratories, LLC 6280 S. Redwood Rd.

Salt Lake City, UT 84123 U.S.A.

Standard Test Protocol (STP) Number: STP0007 Rev 16 Test Procedure(s):

Deviation(s): None

Summary: The VFE test is performed to determine the filtration efficiency of test articles by comparing the viral control counts upstream of the test article to the counts downstream. A suspension of bacteriophage  $\Phi X174$  was aerosolized using a nebulizer and delivered to the test article at a constant flow rate and fixed air pressure. The challenge delivery was maintained at 1.1 - 3.3 x 10<sup>3</sup> plague forming units (PFU) with a mean particle size (MPS) of 3.0 µm ± 0.3 µm. The aerosol droplets were drawn through a six-stage, viable particle, Andersen sampler for collection. The VFE test procedure was adapted from ASTM F2101.

All test method acceptance criteria were met. Testing was performed in compliance with US FDA good manufacturing practice (GMP) regulations 21 CFR Parts 210, 211 and 820.

> Test Side: Inside Test Area: ~7.8 cm<sup>2</sup>

VFE Flow Rate: 28.3 Liters per minute (L/min)

Positive Control Average: 2.3 x 10<sup>3</sup> PFU <1 PFU Negative Monitor Count:

MPS: 3.2 µm





Mikell Goldsberry electronically approved

Study Director Mikell Goldsberry 27 May 2021 00:00 (+00:00)

Study Completion Date and Time

801-290-7500 I

nelsonlabs.com

sales@nelsonlabs.com

FRT0007-0001 Rev 16



## Results:

| Test Article Number | Percent VFE (%)    |
|---------------------|--------------------|
| 1                   | 99.5               |
| 2                   | 99.0               |
| 3                   | >99.9 <sup>a</sup> |

<sup>&</sup>lt;sup>a</sup> There were no detected plaques on any of the Andersen sampler plates for this test article.

The filtration efficiency percentages were calculated using the following equation:

$$\% VFE = \frac{C - T}{C} x \ 100$$

C = Positive control average

T = Plate count total recovered downstream of the test article Note: The plate count total is available upon request

rkw