

Sponsor: Jan Buk Pardam s.r.o. Zizkova 2759 Roudnice nad Labem, Ustecky 413 01 CZECH REPUBLIC

## Viral Filtration Efficiency (VFE) Final Report

Test Article: NnF MBRANE® PA6+Ag

Study Number: 1366181-S01 Study Received Date: 23 Nov 2020

Testing Facility: Nelson Laboratories, LLC 6280 S. Redwood Rd.

Salt Lake City, UT 84123 U.S.A.

Test Procedure(s): Standard Test Protocol (STP) Number: STP0007 Rev 16

Deviation(s): None

**Summary:** The VFE test is performed to determine the filtration efficiency of test articles by comparing the viral control counts upstream of the test article to the counts downstream. A suspension of bacteriophage  $\Phi$ X174 was aerosolized using a nebulizer and delivered to the test article at a constant flow rate and fixed air pressure. The challenge delivery was maintained at 1.1 - 3.3 x 10<sup>3</sup> plaque forming units (PFU) with a mean particle size (MPS) of 3.0 µm ± 0.3 µm. The aerosol droplets were drawn through a six-stage, viable particle, Andersen sampler for collection. The VFE test procedure was adapted from ASTM F2101.

All test method acceptance criteria were met. Testing was performed in compliance with US FDA good manufacturing practice (GMP) regulations 21 CFR Parts 210, 211 and 820.

Test Side: Either
Test Area: ~40 cm<sup>2</sup>

VFE Flow Rate: 28.3 Liters per minute (L/min)

Conditioning Parameters: 85 ± 5% relative humidity (RH) and 21 ± 5°C for a minimum of 4 hours

Positive Control Average: 1.3 x 10<sup>3</sup> PFU Negative Monitor Count: <1 PFU

MPS: 2.9 μm





Curtis Gerow electronically approved for

nelsonlabs.com

Mikell Goldsberry

29 Dec 2020 00:30 (+00:00)

Study Completion Date and Time

Study Director

801-290-7500

sales@nelsonlabs.com

FRT0007-0001 Rev 16 Page 1 of 2



## Results:

Test Article Number	Percent VFE (%)
1	>99.9 <sup>a</sup>
2	>99.9 <sup>a</sup>

<sup>&</sup>lt;sup>a</sup> There were no detected plaques on any of the Andersen sampler plates for this test article.

The filtration efficiency percentages were calculated using the following equation:

$$\% VFE = \frac{C - T}{C} x \ 100$$

C = Positive control average

T = Plate count total recovered downstream of the test article Note: The plate count total is available upon request

szh